

These are great fun and quick projects. Forms use MosaicStone Cement™ (regular cement will crack). The MosaicStone Cement™ dries quickly to a smooth white finish and is extremely durable. A finishing topcoat is optional. Self-adhesive felt may be applied to the bottom of the coasters.

***Please read all directions before beginning. Enjoy!***

**Included in Kit:**

- 12 Square reusable coaster molds
- 2 lb MosaicStone Cement
- 1 lb of Stained Glass Square Variety

**Additional List (not included in kit):**

- Pen
- Scissors
- Contact Paper
- Petroleum Jelly
- Paper Towel
- Measuring Cup
- Mixing Bowl and Spoon

**Indirect Mosaic Method - Directions:**

**Step 1 - Preparation**

1. Trim a piece of clear contact paper to the size of the square pattern (contact available from stained glass and craft suppliers and grocery stores). Note that the contact paper should be smooth, sticky and free of creases.
2. Contact paper should fit closely inside the mold. Achieve a good fit by placing the trimmed contact paper inside the mold and running a pen along the sides of the mold wherever the contact needs to be further trimmed. Trim as needed and place contact to the side.
3. Using a paper towel, apply a thin coat of petroleum jelly along the inner edges of the mold.

**Step 2 – Place Glass**

1. Peel the backing off the contact paper and place in the mold sticky side up.
2. Place stained glass pieces on the contact paper. Place pieces slightly apart and in from the mold's edge to allow room for cement.
3. Adjust pieces as necessary and press them firmly onto the contact paper.

**Step 3 – Pour Cement**

1. Mix 6 tablespoons of MosaicStone Cement with 7 teaspoons of water per coaster. If you wish to color your cement, add Mosaic Art Colorants to the water before mixing. Consistency should be similar to pancake batter (adjustments may be necessary due to climate). Place the remaining MosaicStone Cement powder off to the side.
2. Pour cement slowly and evenly into the mold. Do not move the mold while the cement is drying.
3. Tap the table underneath the mold for two to three minutes to release any air bubbles in the cement.
4. Wait approximately thirty minutes to one hour (time may vary due to climate) for the cement to harden. The cement will warm as it hardens. Once it has cooled and set remove the coaster from the mold.
5. Remove the coaster by turning the mold over and lifting up the edges of the mold.
6. Peel off the contact paper and clean off any excess cement covering the glass. You may clean the cement with a paper towel, sponge or craft knife.
7. Fill in any remaining air holes by mixing up a small amount of the remaining MosaicStone Cement into a paste and rubbing the cement into the holes in a circular motion. If your project gets any marks or you have contact lines on the cement you may smooth the cement out with sandpaper.
8. Repeat steps for the remaining coasters.
9. Allow coasters to cure for 24-48 hours. Self-adhesive felt or rubber feet may be applied to the backs of the coasters.

**WARNING:** Eye Irritant. **Precautions:** Keep away from eyes. **First Aid:** If eye contact occurs, rinse with tap water for 5-10 minutes. If irritation persists, seek medical attention. For further health information, contact your local poison control center. Note: This product contains crystalline silica sand which is known in the State of California to cause health issues.

Questions? Call 800-937-9593 or (813) 806-2923 outside the US or e-mail [info@dticrafts.com](mailto:info@dticrafts.com)

Copyright 2000 Diamond Tech All Rights Reserved.

For more mosaic ideas visit DTI online at [www.DiamondTechCrafts.com](http://www.DiamondTechCrafts.com)